



PO Box 707 ♦ Downingtown, Pennsylvania 19335

610-518-2519 (office) ♦ 610-518-2517 (fax)

POLYETHYLENE GLYCOLS (PEG)

SALES SPECIFICATIONS:

<u>PROPERTY</u>	<u>PEG-200</u>	<u>PEG-300</u>	<u>PEG-400</u>	<u>PEG-600</u>
Specific Gravity	1.124	1.125	1.126	1.126
Viscosity, cst @ 25 C	40-50	60-70	80-90	120-135
Hydroxyl Number	534-591	356-394	267-295	178-197
Avg. Freeze Point, C	-50	-10	6	22
Solubility in Water	infinite	infinite	infinite	infinite
Appearance @ 25 C		Free and clear, liquid		
pH	6.0-7.5	6.0-7.5	6.0-7.5	6.0-7.5
% water, wt (max)	0.5	0.5	0.5	0.5
Color, Pt-Co, @ 25 C	25	25	25	25
Molecular Weight	190-210	285-315	380-420	570-630

January 24, 2002